



Duffelsesteenweg 156
 B-2550 KONTICH
 Tel : 0032 (0)3 458 44 96
 Fax : 0032 (0)3 458 44 97
 VAT : BE0450874212
 RPR Antwerp
www.eco-colors.com
info@ecocolors.be

Technical data sheet **Acrylic wall primer**

Type	Water-based acrylic wall primer	
Application	Wall primer for interior and exterior application.	
Codification	WML-9999 : transparent WMP-1000 : white WMP-1200 : white, thixotropic	
Features	Compensates the differences in intake of the surface. For a nice, smooth end result. For a significantly lower consumption of the finishing paint. Suitable for damp locations. For interior and exterior application.	
Technical	Appearance	: transparent or white liquid
	Density	: appr 1.00 kg/lt WML-9999 appr 1.40 kg/lt WMP-1000
	Solids (in weight)	: appr 50.50 % WML-9999 appr 57.75 % WMP-1000
	Drying period (20°C / 65 % RH)	: dust free : appr 15 min finishing : appr 2 hours
Processing details	Environmental conditions	: temperature between 15 and 25°C air humidity between 40 and 70 % RH
	Dilution	: water
	Cleaning	: water
	Return	: theoretical : 6-8 m ² /lt (depends on method of application, quality of substrate and shape of object)
	Remark	: blend well before usage
Method of application	Airless, brush/paint roller	

Substrat	Various mineral surfaces (plaster, gyproc, cementation). The substrate has to be free of any dust, fat and other contaminations.
Storage life	Minimum 12 months, in unopened, original packing, stored at a cool, dry and frost-free place.
Safety information	Check safety data sheet Storage, use and removal according to local regulations. This product is not allowed to end up in the sewer system.

Free of VOC.

The information in this data sheet is not intended to be exhaustive. Any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. All products supplied and technical advice given are subject to our Conditions of Sale. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development.